

BX EPOKSIEN TYÖ- SEKÄ KOVETTUMISAJAT

EPOKSI	Työaika 22°C	Kovettumisaika 22°C	Kovettumisaika 50° / 60°C
BX10	10-12 min	2 - 2,5 h	20 min / 15 min
BX15	15-18 min	3 h	25 min / 20 min
BX30	25-30 min	8 h	90 min / 50 min
BX60	55-65 min	18 h	180 min / 100 min
BX180	2,5 – 3,0 h	24 h	180 min / 100 min

the choice of professionals.

